

# PLASPERTEX PAINT CO LTD

## Technical Product Data sheet

09.11

Product Name	Plasroof
Product reference	PP06
Product description	Highly flexible water borne roof coating based on a modified VA polymer, providing a waterproof seamless membrane onto a wide range of roofing surfaces. Plasroof should not be used on roofs liable to ponding.
Uses	Decoration and protection of a wide range of roofing surfaces
Pack sizes availability	5, 10 litres
Colour range	White. Red. Black. Brown. Grey. Special colours on request subject to minimum batch sizes
Specific gravity	Approx 1.3
Flash point	Non flammable
Recommended Spreading rate	1.125 m <sup>2</sup> /litre applied over two coats
Solids content	Approx 57% w/w Approx 44% v/v
Drying time	Approx 4 hours 20°C 65%RH
Over-coating time	Approx 6-8 hours 20°C 65%RH
Minimum application temperature	Air and surface temperature should be 5°C and rising. Do not apply during damp or frosty weather or when rain is imminent
Recommended dry film thickness	Approximately 400 microns
Method of application	Brush, roller or airless spray
Preparation	Surfaces must be clean, sound and dry and prepared in accordance with BS6150 Painting of buildings – code of practice. Bare metal surfaces must be adequately primed.
Storage life	Min 12 months in original sealed containers. Protect from frost and direct heat
Thinning/cleaning	Thin where necessary with clean water. Do not exceed 1 part water to 10 parts of Plasroof. Wash equipment immediately after use with water and detergent
Safety precautions	Refer to the safety data sheet before use
Volatile organic content (voc)	Limit for this product Cat A/i 140g/l (2010). This product contains maximum 20g/l VOC
Disposal	As supplied or containing liquid product – non hazardous waste code 08 01 12 waste paint and varnish other than those mentioned in 08 01 11 Used containers drained/rigorously scraped out and containing only dry residues: categorised as non-hazardous with waste code 15 01 02 (plastic package) and 15 01 04 (metal package)

