

# PLASPERTEX PAINT CO LTD

## Technical Product Data sheet

07.12

|                                 |   |
|---------------------------------|---|
| Product Name                    | Plaspertex Spray Textured Masonry Paint   |
| Product reference               | PP01  |
| Product description             | A highly durable long life spray applied textured coating for the protection and decoration of most external masonry surfaces.<br>Plaspertex Spay Textured masonry paint is a solvent borne high build product based on plasticised alkyd technology with reinforcing fibres. Contains a fungicide to inhibit mould growth on the surface<br>Available in coarse texture (Grade 25) medium texture (Grade 15) and fine texture finishes     |
| Uses                            | Long life exterior masonry decoration and protection  |
| Pack sizes availability         | 20 litres   |
| Colour range                    | White plus 12 standard colours. Special colours on request subject to minimum quantities.   |
| Specific gravity                | Approx 1.2  |
| Flash point                     | Flammable Flash point approx 40deg C  |
| Recommended Spreading rate      | Approx 1.25 litres/m <sup>2</sup> (16 m <sup>2</sup> per 20 litre container)  |
| Solids content                  | Approx 75% w/w<br>Approx 60% v/v  |
| Drying time                     | Approx 24 hours 20°C 65%RH (2 – 3 weeks for full cure)  |
| Over-coating time               | Approx 24 hours 20°C 65%RH  |
| Minimum application temperature | Do not apply during frosty or foggy weather or onto damp surfaces   |
| Recommended dry film thickness  | Approximately 750 microns   |
| Method of application           | Air assisted airless (Graco President 10:1 HMSU) or hopper spray  |
| Preparation                     | Surfaces must be clean, sound and dry and prepared in accordance with BS6150 Painting of buildings – code of practice.<br>Treat organic growth with fungicidal solution.<br>Remove any unsound previous coatings and weak material and repair with suitable exterior repair products before coating with Tinted Stabiliser.   |
| Storage life                    | Min 12 months in original sealed containers. Protect from frost and direct heat   |
| Thinning/cleaning               | Thin where necessary with D40 Solvent or white spirit. Do not exceed 1 part solvent to 20 parts of coating.<br>Wash equipment immediately after use with D40 solvent or white spirit.   |
| Safety precautions              | Refer to the safety data sheet before use   |
| Volatile organic content (voc)  | Limit for this product Cat A/c 430g/l (2010).<br>This product contains maximum 300g/l VOC   |
| Disposal                        | When this coating, in its liquid state, as supplied or skinned, becomes a waste, it is categorised as hazardous waste, with code 08 01 11 (list of hazardous wastes)<br>Used containers, drained and/or rigorously scraped out and containing dried residues of the supplied coating, are categorised as non-hazardous waste, with code 15 01 04 (list of wastes)<br>If mixed with other wastes the above waste codes may not be applicable |

